

A New Concept in Multi-layer Coating of Steel Pipes

When it comes to laying pipes without cutting a trench, a large number of coating variants are already established on the market. These include coating systems with an additional coating layer for mechanical protection, like cement mortar or glass fibre reinforced plastics. 3-layer polyethylene or polypropylene coatings with increased thickness are also commonly used. These thick-layer coatings are usually produced in several coating steps, with the best possible adhesion between the layers. In this situation the 3-layer polyolefin coating with increased thickness has to provide effective corrosion protection and advanced mechanical protection. This article explains the disadvantages of this concept and offers an alternative coating system.

Over the course of time, methods of trenchless laying of pipes have been growing steadily in importance. There is hardly any major project which does not involve the crossing of roads, railway lines, rivers or streams and possibly also protected nature reserves. From the financial point of view, such situations can only be resolved by construction methods which do not involve cutting trenches. Such special construction procedures require independent planning, which sets them apart from conventional pipe-laying situations which can be resolved with standard pipes and pipe coatings.

There are a number of different coating systems available for special construction techniques, but the selection of the coating system is usually determined by the experience of the planners or the company carrying out the work. The use of thick-layer coatings, especially on a polypropylene base, has gained wide acceptance in the jetting technique sector in particular. In the case of cross-head extrusion two or even three production stages are required depending on the polypropylene (PP) layer thickness. A disadvantage with polypropylene is inadequate strength at low temperatures. Experiences with this have been reported in the past [1].

Polypropylene becomes brittle at lower temperatures. Local stress peaks, caused for example by point layering or point loading, are dissipated in the brittle state in the form of cracks, in particular if there is previous damage such as scoring or notching. The damage shows that, if cracks form, the good adhesion between the polypropylene layers represents a serious disadvantage, because the entire layer is affected by

the crack formation. This of course also applies to thick-layer coatings which are produced in one step.

For aged 3-layer PP coatings this usually gets even worse. As the coatings become older, the brittleness temperature shifts to higher values in the course of time. The issue of crack formation is therefore a question of time, depending on the load situation and the plastic base. In the case of trenchless pipe laying in particular, a critical combination of scoring and notching, as well as point loading, cannot be excluded. Recent investigations showed crack propagation between coating layers in the case of interlayer adhesion. In the case of missing adhesion between coating layers crack propagation from one layer to another was not observed so far. With trenchless laying methods there is the risk that without strong interlayer adhesion the coating could be peeled off when the pipe is drawn into position. In order to compensate missing interlayer adhesion good shear strength of the coating is required, what seems at the first glance confusing. In the following section we shall therefore take a closer look at these concepts in the context of claddings and coatings of steel pipes.

ADHESION AND SHEAR STRENGTH

High peel strength, which means good adhesion, is drawn on as a quality feature for the three-layer polyethylene or polypropylene coatings conventionally used today, consisting of epoxy resin primer, adhesive, and the polyethylene or polypropylene top layer. Technical delivery specifications, such as DIN 30670 [2] or DIN 30678 [3], require for the determination of the peel strength a separation within the adhesive layer (cohesive failure). With a multi-layer structure, separation always occurs in the weakest element. This means that, with a separation inside the adhesive layer, the adhesion of the coating to the steel and the adhesion of the individual components to one another is greater than the strength of the adhesive used. The adhesion of the coating to the steel is determined by the bond of the epoxy resin primer and the steel, and is comparable to a single-layer coating of the epoxy resin. High values for the peel strength with a separation within the adhesive layer are indicative that the three-layer coating has been properly produced, and also of good adhesion of the coating.





Figure 1: Differences in measurement of adhesion and shear strength



Figures 2 and 3: Test principle for determining adhesion and shear strength in accordance with AS/NZS 1518 [5]

Experimental determinations of the adhesion all adopt the same principle: A force takes effect vertically on a defined surface area of the coating. The amount of the force which is required to separate the coating from the steel surface is taken as the measure of adhesion. The adhesion of a single-layer epoxy resin coating is determined, for example, by the pull-off test according to DIN EN ISO 4624 [4]. The measured value then only corresponds to the adhesion if the separation takes place between the coating and the steel (adhesive failure). A separation inside the layer (cohesive failure) in this case also means that the adhesion is greater than the strength of the coating material.

While in the case of adhesion the force imposed vertically to the coating is countered by a resistance, when it comes to the shear strength this resistance takes effect in the longitudinal direction (**Figure 1**). Forces in the longitudinal direction to the axis of the pipe are to be anticipated in particular with trenchless pipe laying, while the pipe is being drawn in. In this situation, adhesion and shear strength are not necessarily to be equated with one another in the physical sense.

The difference between these two values is particularly clear in the case of AS/NZS 1518 [5], an Australian delivery specification for two-layer HDPE coatings consisting of adhesive and HDPE top layer. Here, the two values are assessed separately. The adhesion is determined by a peel test. To do this, a 25 mm wide strip of the coating is cut into. For the purpose of the test, a 300 g weight is hung on the end of the strip. For the assessment, the peeling speed is determined, which may amount to 100 mm/min at room temperature. The principle of this test is shown in **Figure 2**.

To determine the shear strength, AS/NZS 1518 makes reference to an American test specification, ASTM D 1002 [6]. For the test, a defined adhesion surface is produced with the

adhesive of the two-layer coating between two metal plates. In a tensile test, the force necessary to break the adhesion is then measured (**Figure 3**). For the shear strength of the adhesive, AS/NZS 1518 requires a minimum value of 34 N/cm². In a similar way, for example, the shear strength of FBE is also determined in accordance with DIN EN 1465 [7].

Another test principle for determining the shear strength is applied in the case of the cement mortar coating of PE or PP sheathed (polyolefin sheathed) pipes. In the case of the special design (Type S) for trenchless laying procedures, a corresponding shear strength of the coating is again required. The technical delivery specification, DVGW¹ worksheet GW 340, also makes provision in this situation for a component test [8]. In this case, the system of steel base material, coating, and sheathing is not subjected to a tensile load but to a pressure load parallel to the axis of the pipe (**Figure 4**).

The combination of cement mortar and polyolefin layer in




Figure 4: Test arrangement for determining the shear strength in accordance with DVGW worksheet GW 340

¹ DVGW German Association for Gas and Water




Figure 5: Shear strength and adhesion in the context of a rough surface structure

particular demonstrates that an adhesion deficiency does not necessarily also mean a deficiency in shear strength. Naturally, between cement mortar and polyolefin layers there is only the possibility of a mechanical link. In the case of the FCM-S format according to DVGW worksheet GW 340, adhesion and shear strength are achieved by appropriate profiling of the polyethylene coating. In this situation a longitudinal rough T-shaped profile is extruded, in which the cement mortar coating can engage.

As well as the extrusion of a rough T-profile, which by its nature allows for both adhesion as well as shear strength, the use of what is referred to as a "rough coat" is known. The rough coat arrangement of the polyethylene coating is specifically aimed at increasing the shear strength of a concrete sheathing which is usually reinforced with steel inlays. This coating format is often used for offshore pipe laying. After the extrusion of the polyethylene layer, a fine PE granulate is then sprinkled onto the still hot coating. The granulate melts on, and a rough surface structure is formed. This profiling achieves a perceptible shear resistance

by mechanical means (**Figure 5**). Adhesion is not provided, however. Particular attention was paid to this effect in particular in the development of alternative multi-layer systems for trenchless pipe laying methods.

THE ALTERNATIVE COATING CONCEPT

The main idea in the development of an alternative coating system is to apply the top layer without adhesion to the other layers in a multi-layer structure, in order to avoid the propagation of cracks between these layers. The crack formation is accordingly stopped in the area of the boundary surface between two non-adhering layers. In this situation, however, a corresponding shear strength should still be ensured. In principle, this core concept is already provided in the case of cement mortar coatings. Up to now, this formulation has not been considered in the case of 3-layer polyolefin coatings with increased thickness, which are often preferred.

This new coating concept presented here makes use, instead of cement mortar, of an extruded Polypropylene or polyamide top layer, which does not adhere to the coating layers below. This can be achieved by extrusion of a polypropylene or polyamide layer on the top of a three-layer polyethylene coating modified by a rough coat, which forms an independent mechanical means of protection (Figures 6 and 7). In the case of a polypropylene top layer, the selection of an appropriate application temperature prevents adhesion to the polyethy-




Figure 6: Structure of the multi-layer coating




Figure 7: Underside of the polyamide layer

lene layer. For a polyamide top layer, the combination of non-polar polyethylene layer and polar polyamide top layer prevents the adhesion between both coating layers. In this multi-layer structure, therefore, as in the case of cement mortar, the functional aims of corrosion protection and that of mechanical protection are specifically separated from one another.

PROPERTIES OF THE NEW COATING CONCEPT

Shear strength of the coating

The coating combination of polyethylene, rough coat and polyamide or polypropylene top layer was investigated to determine the shear strength on the basis of the GW 340 worksheet [8]. To do this, the protective sheath on the corrosion protection coating was pushed off by a ring segment adapted for the purpose and the force required was recorded (**Figure 8**).

To test the multilayer system of a 3-layer polyethylene coating with an additional polyamide top layer respectively with an additional polypropylene top layer, pipe segments about 5 cm wide were cut. The top layer was cut on both ends of the pipe segment, so that a ring with a breadth of 25 mm was remaining. On the upper end the coating was removed as far as the polyethylene layer and at the lower end as far as the epoxy resin (**Figures 9** and **10**).

A steel ring, matched to the outer diameter of steel and polyethylene coating, allows by its projection for a shear area of some 5 mm (**Figure 8**). The principle is adopted that the measurement is ended after the shearing of an area of 5 mm. The specimen and the ring set on it are positioned beneath the testing device and the force necessary for the shearing is recorded. The combination of polyethylene and polyamide could not be completely pressed off in this situation in the intended test area due to lack of projection of the ring segment. The shear forces determined therefore represent minimum values, which in practice are higher. For the 25 mm wide coating strip, with a test surface of 175 cm^2 , a force of 3.6 tons was nevertheless determined. The shear strength to be demonstrated according to the DVGW worksheet GW 340 therefore reaches at least 200 N/cm^2 .

In the case of the polyethylene and polypropylene combination it was possible to determine the actual shear force with the selected test setup. Due to the profiling of the PE coating, in the case of non-adhering coating and with the same geometries, a force of just on 6 tons was determined corresponding to a shear strength of




Figure 8: Set up for testing the shear strength

340 N/cm^2 in accordance with DVGW worksheet GW 340. The minimum shear strength of 50 N/cm^2 required according to DVGW worksheet GW 340 [8] for cement mortar sheathings of Type S is well exceeded by both coating variants.

Although the shear strength of the new coating system is only attained by mechanical means, it is approximately on the same level as the values published in the literature for three-layer polyethylene coatings. For the three-layer polyethylene coating shear strengths are determined of between 300 and 400 N/cm^2 [9] at room temperature.

Crack formation in the multi-layer system

With the aid of an impact test at low temperatures, the crack formation in the multi-layer system was examined in greater detail. Because the PP coating reacts perceptibly more sensitively to cold in comparison with the polyamide, for the test the combination of polyethylene and polypropylene was selected. The impact test is performed in this situation under perceptibly more stringent conditions as described in the delivery specification for polypropylene coatings (see DIN 30678 [3]). The test is carried out with an impact force of 200 Nm (as opposed to 10 Nm according to DIN 30678) at sub-zero temperatures (as opposed




Figure 9: Test specimen, PE/PP combination




Figure 10: Test specimen, PE/PA combination




Figure 11: Drop weight



Figure 12: Result of the impact test

to 0°C according to DIN 30678), in order deliberately to provoke cracks. The drop weight in this situation is not a hemisphere as provided for according to DIN 30678. The test surface area has a flattened form, with a diameter of 21 mm (**Figure 11**).

The aim of this impact test is to clarify the issue of whether, with the multilayer structure, a crack which forms in the outer layer can be transferred over the bounda-

ry surface into the polyethylene located beneath. While with the same test arrangement cracks are produced in the pure PP coating as early as at -10°C [1], in the multilayer system they first occur at -60°C, which may possibly be attributable to the buffer effect of the polyethylene coating, which has a tendency to be softer. As anticipated, the polyethylene coating in this layer arrangement remains undamaged. In **Figure 12**, after the impact test, in the area of

the crack only the black rough coat can be seen beneath the detached polypropylene coating. The cracks end, as expected, in the boundary surface of the polyethylene and polypropylene.

Testing the gouge resistance

For the simulation of the loadings imposed during a draw-in procedure, what is referred to as the gouge test was selected, in accordance with the Canadian Standard CAN CSA Z 245.20-10 [10]. As a model presentation for this test, the effect of a sharp stone was chosen, over which the pipe is pulled as it is being drawn into the bore channel. Accordingly, a sheathed pipe specimen is drawn under a test tip (**Figure 13**) over a length of 50 mm.

For this purpose, the test tip is weighted with a weight of 50 kg (angle of the test tip 20°, hemisphere 2.5 mm diameter). The advance of the sheathed pipe specimen was at a rate of 200 mm/min. The penetration depth is determined with the aid of a dial gauge. **Figure 14** shows the results of these measurements. The polyamide and glass fibre reinforced plastic layers differ markedly from the polyethylene and polypropylene layers. The indentation resistance of the polyamide coating in this situation is almost at the level of a glass fibre reinforced coating. This test provides impressive proof that the polyamide coating can tolerate perceptibly greater loads in comparison with polypropylene and confirms the advantages of polyamide already described earlier [11], [12].

PRACTICAL EXPERIENCES

The coating combination of PE and PA in plough laying

As part of a program of upgrading and extension, the Bavarian Forest Water Board carried out the construction of a mains water pipe to provide the towns and municipalities of the catchment areas south of the Danube with drinking




Figure 13: Test tip




Figure 14: Results of different coatings in the gouge test (Test in accordance with CAN CSA Z 245.20-10 [10])

water from the groundwater pumping station at Moos near Plattling in the south of Germany. The pipeline construction project, planned for the period from April to August 2011, covered a trace length of 9.5 km. Because of the condition of the soil, the companies involved had already decided at the planning phase to lay a large part of the whole distance by means of a plough procedure.

The plan was for about half of the planned pipeline route to be laid in this manner. This was subdivided into 21 individual sections, with a maximum draw-in length of 760 m. For the first time a multi-layer system consisting of polyethylene and polyamide was used over a 1200 m long part of the pipeline. The pipes were welded into strings on the trace itself, and mounted on roller stands for drawing in. For the subsequent coating, the connection areas were sand-blasted and provided with shuttering to accommodate a polyurethane casting compound.

For the laying, a 480 h.p. winch with a pulling power of max. 220 tonnes was used (**Figure 15**). This winch draws the laying plough, which brings the pipe to a laying depth of maximum 2.5 metres. The tip of the plough clears out and shapes both the cavity as well as the bed for the pipe string. Taking account of a curve radius provided for of 190 metres, incurred due to the procedure, the pipe format selected can be subjected to a maximum tensile force of 100 tonnes. These forces, however, were not attained even with a draw-in length of 760 metres. The maximum tensile force never exceeded 60 tonnes. A major part was played in this on the one hand by the amenable soil conditions, but on the other also by the low slide friction of the plastic coating.

The coating combination of PE and PP in the HDD process

As part of a relaying project to supply a hotel complex in the northern part of the city of Münster, in response to an order by the municipal public works department, a gas pipe with a rated diameter of 200 was laid beneath an area of woodland and the hotel's own tennis court. The jetting process is especially well-suited for situations such as these.

By contrast with the plough method described earlier, laying with the HDD process or jetting has been known for a long time (**Figure 16**). While with ploughing the pipe string is, as a rule, drawn dry into the soil, with the jetting technique a bentonite solution provides, in the ideal situation, for a floating introduction into the ground. The start of the project was in March/April 2013. The pipes, provided with a combination of polyethylene and polypropylene, were welded to form a string.

In order to protect the connection areas, a subsequent coating was provided on a glass fibre rein-forced plastic base. The pipe drawing took place in September 2013.



Figure 15: The coating combination of polyethylene and polyamide in the plough laying procedure



Figure 16: The coating combination of polyethylene and polypropylene in the jetting process

The horizontal bore, some 2.5 metres deep, was 60 metres long. The pipe string was then guided under a wall, which was protected as an ancient monument, and then integrated into the existing network.

CONCLUSIONS

When it comes to trenchless construction procedures, there are a number of different concepts to choose from with regard to coatings and sheathing. Thick-layer coatings frequently used for this purpose are combining corrosion protection and mechanical protection. Experiences in the recent past show that in case of fracture mechanical properties the view cannot remain restricted to the product with as-new values alone; it is essential

to take account also of the changes to these materials which are wrought by time. Mechanical loadings, which do not cause any problems for material of new value, can lead in later operation to crack formation. In thick layer systems these cracks extend to the steel base material, so the function of passive corrosion protection is no longer provided.

For polyethylene or polypropylene coated pipes, which are additionally sheathed with cement mortar, the function of corrosion protection and of mechanical protection have always been separated from one another. In the event of flexure, for example, which can occur during handling on site, crack formation in the cement mortar sheathing is by no means uncommon. The reinforcement of the sheathing with fibres and fabric strips serves in this situation to bridge the cracks, so the cement mortar is fixed on the pipe surface. Because cement mortar and polyethylene do not enter into a substance combination, cracks in the mortar are of no significance for the function of corrosion protection.

With the new multi-layer coatings presented here, by the specific selection of the coating materials and, as appropriate, the manufacturing parameters, this concept of separation of the functions of corrosion protection and mechanical protection is transferred to pure plastic coating systems. The shear strength required for the application sector of trenchless laying is realized by the rough coat and the mechanical engagement of the layers associated with this.

Initial experiences with applications show that during laying no impairments can be identified in comparison with the thick-layer systems used hitherto. Advantages in long-term service life are to be anticipated in case of scoring and/or notching, as well as point loadings or point layering, which are typical loads for trenchless laying of pipes. In the event that, in the course of time, due to age-induced brittleness, forces from point loadings and point layering are dissipated by crack formation in the outer cover layer, the coating will nevertheless remain stable in form due to the soil pressure imposed. The function of corrosion protection of the underlying coating layer will not be impaired. In this situation, the newly-developed multi-layered systems are plainly superior to the thick-layer systems used hitherto, and so expand the product spectrum of special solutions for pipeline construction.

LITERATURE

- [1] H.-J. Kocks, C. Bosch, M. Betz; "Fracture mechanical properties of polyolefin: Do the standards specify realistic areas of application?", 3R international 50 (2011) Special Edition 1, p. 80 – 87
- [2] DIN 30670: Polyethylene coatings of steel pipes and fittings; requirements and testing, DIN Deutsches Institut für Normung e. V. (2012)
- [3] DIN 30678: Polypropylene coatings of steel pipes and fittings; requirements and testing. DIN Deutsches Institut für Normung e. V. (2013)
- [4] DIN EN ISO 4624: Paints and varnishes – Pull-off test for adhesion, ISO (2003)
- [5] AS/NZS 1518: External extruded high-density polyethylene coating systems for pipes, Standards Australia/Standards New Zealand (2002)
- [6] ASTM D 1002: Standard Test Method for Apparent Shear Strength of Single-Lap-Joint Adhesively Bonded Metal Specimens by Tension Loading (Metal-to-Metal), American Society for Testing and Materials (2010)
- [7] DIN EN 1465: Adhesives – Determination of lap-shear strength of rigid-to-rigid bonded assemblies, DIN Deutsches Institut für Normung e. V. (2009)
- [8] DVGW Worksheet GW 340: FCM sheathing for mechanical protection of steel pipes and fittings with polyolefin coatings, DVGW German Association for Gas and Water (04-1999)
- [9] S. W. Guan, P. Mayes, A. Andrenacci, D. Wong: ADVANCED TWO LAYER POLYETHYLENE COATING TECHNOLOGY FOR PIPELINE PROTECTION, Corrosion Control 2007, Sydney, Australia, November 25, 2007
- [10] CAN CSA Z 245.21-10: Plant-applied external polyethylene coating for steel pipe, Canadian standards association (May 2010)
- [11] M. Hartmann, H.-J. Kocks, S. Maier; „Polyamide coatings for non-conventional pipe laying methods“; 3R international 50 (2011) Special Edition 2, p. 36 – 43

AUTHORS



Dr. HANS-JÜRGEN KOCKS

Salzgitter Mannesmann Line Pipe GmbH
Siegen, Germany
Phone +49 271 691-170
E-Mail: hans-juergen.kocks@smlp.eu



Dr. MARKUS BETZ

Salzgitter Mannesmann Forschung GmbH
Duisburg, Germany
Phone +49 203 999-3113
E-Mail: m.betz@du.szmfd.de



RALF NORDMANN

Salzgitter Mannesmann Line Pipe GmbH
Siegen, Germany
Phone +49 271 691-246
E-Mail: ralf.nordmann@smlp.eu

IPC 2014 IPE



INTERNATIONAL PIPELINE CONFERENCE & EXPOSITION

CHALLENGING PIPELINE PERFORMANCE



THE CONFERENCE

September 29 - October 3, 2014

The Hyatt Regency Hotel & TELUS Convention Centre
Calgary, Alberta, Canada

**The definitive conference for
pipeline professionals. Don't miss
this five-day experience!**

300 Attend 13 Technical
Tracks with 300+
presentations, keynotes
and tutorials.

1,500 Network with over 1,500
industry professionals
at sessions and official
functions.

45 Join representatives
from 45 countries
spanning the globe.



THE EXPOSITION

September 30 - October 2, 2014

TELUS Convention Centre
Calgary, Alberta, Canada

**Participate at the world's leading
marketplace for pipeline
technology and services!**

Visit 200 companies
exhibiting today's
foremost technologies,
products and services.

Connect with 5,000
registrants— technical
leaders and business
executives.

Source from a global
marketplace converging
from 30+ countries.

internationalpipelineconference.com



[f](https://www.facebook.com/IPC_Calgary) [in](https://www.linkedin.com/company/international-pipeline-conference-expo) [@IPC_Calgary](https://twitter.com/IPC_Calgary)

internationalpipelineexposition.com

[in](https://www.linkedin.com/company/international-pipeline-exposition) [@petroleumshow](https://twitter.com/petroleumshow)



Conference Patrons



canadian
energy
pipeline
association
l'association
canadienne
des pipelines
d'énergie

ASME
PIPELINE SYSTEMS DIVISION

Media Sponsor



Major Exposition Sponsors



RTD



PII Pipeline Solutions
a GE Oil & Gas and Al Shafeen joint venture

